



# Anjani Portland Cement Ltd

Anjani Cement Center, Plot No. 7 & 8 Nagarjuna Hills, Punjagutta, Hyderabad 500 082. AP

## Ordinary Portland Cement 43 Grade Test Certificate

Date of Despatch: 15/05/2015

Ref.: APCL / QC / TEST

Week No: 20

Particulars	Test Result	Requirement. as per IS 8112 : 1989
<b>Chemical</b> (as per IS : 4032-1985)		
• LOI (%)	1.98	4.0 Max
• I. R (%)	3.11	4.0 Max.
• SO <sub>3</sub> (%)	2.36	3.5 Max
• MgO(%)	0.74	6.0 Max
• Chloride (%)	0.004	0.10 Max
• LSF	0.88	0.66 to 1.02
• A/F	1.30	0.66 Min
<b>Physical</b> (as per IS : 4031-1988)		
• Spec. surface (M <sup>2</sup> /kg)	289	225 Min.
<b>Soundness</b>		
• Lechatlier (mm)	01	10 Max.
• Autoclave (%)	0.048	0.8 Max.
<b>Setting Time (minutes)</b>		
• Initial	125	30 Min.
• Final	265	600 Max.
<b>Compressive Strength (M. Pa.)</b>		
• 3 days	35.2	23 Min.
• 7 days	43.7	33 Min.
• 28 days	57.2	43 Min. } 58 Max. }

Certified that the cement complies with IS 8112 : 1989

A.Mgr (Q.C)

G. M (Q. A)