



An ISO 9001:2015 Company

# Anjani Portland Cement Limited

( A Subsidiary of Chettinad Cement Corporation Pvt Limited )

## PPC Test Certificate

Ref.: APCL/QUAS/TEST / W.No:04

Date of Despatch: 22.01.2023

Particulars	Test Result	Requirement as per IS 1489(Part-1) : 2015
<b>CHEMICAL ( As per IS: 4032-1985)</b>		
<ul style="list-style-type: none"><li>LOI (%)</li><li>I.R. (%)</li></ul>	3.24 30.29	5.0 Max. Max: $X+4(100-X)$ 100 Min : 0.60 x X (Where X is Declared % of Fly ash)
<ul style="list-style-type: none"><li>SO<sub>3</sub> (%)</li><li>MgO (%)</li><li>Chloride (%)</li><li>Declared percentage of Pozzolana (%)</li></ul>	2.24 1.19 0.02 33.0	3.0 Max. 6.0 Max. 0.10 Max. Min-15%,Max-35%
<b>PHYSICAL (As per IS: 4031-1988)</b>		
<ul style="list-style-type: none"><li>Fineness (M<sup>2</sup>/Kg)</li></ul>	346	300 Min.
<b>SOUNDNESS:</b>		
<ul style="list-style-type: none"><li>Le-Chatlier (mm)</li></ul>	01	10 Max.
<ul style="list-style-type: none"><li>Autoclave (%)</li></ul>	0.016	0.8 Max.
<b>SETTING TIME (Minutes)</b>		
<ul style="list-style-type: none"><li>Initial</li></ul>	160	30 Min.
<ul style="list-style-type: none"><li>Final</li></ul>	255	600 Min.
<b>COMPRESSIVE STRENGTH (M Pa)</b>		
<ul style="list-style-type: none"><li>3 Days</li><li>7 Days</li><li>28 Days</li></ul>	23.1 32.8 46.4	16 Min. 22 Min. 33 Min.

Certified that the cement complies  
With IS 1489 (Part - 1) : 2015

A.G.M (QUAS)

Unit Head

Works : Anjanipuram, Gudimalkapuram(P), Cinthalapalem(V&M), Suryapeta (Dist), Telangana State – 508246  
Head Office : # 6-3-553, Quena Square – 4<sup>th</sup> floor ,E3 & E4 ,Erramanzil , Somajiguda , Hyderabad -500 082,Telangana,INDIA.