



**ANJANI
PRATHISTTA**
RAPID HARDENING
PORTLAND CEMENT



Anjani Portland Cement Limited

(A Subsidiary of Chettinad Cement Corporation Limited)

TEST CERTIFICATE

Ref: 1APCL/QUAS/TEST/ W.No: 16

Date of Despatch: 19.04.2017

Particulars	Test Result	Requirement as per IS 8041 : 1990
CHEMICAL (As per IS: 4032-1985)		
• LOI (%)	0.98	5.0 Max.
• I.R. (%)	1.02	4.0 Max.
• SO ₃ (%)	2.16	2.50 % Max. (When C3A ≤ 5 %) 3.00 % Max. (When C3A ≥ 5 %)
• MgO (%)	0.75	6.0 Max.
• Chloride (%)	0.01	0.05 Max.
• L.S.F.	0.87	0.66 to 1.02
• A/F	1.18	0.66 Min.
PHYSICAL (As per IS: 4031-1988)		
• Spec. Surface (M ² /Kg)	360	325 Min.
SOUNDNESS:		
• Le-Chatlier (mm)	01	10 Max.
• Autoclave (%)	0.077	0.8 Max.
SETTING TIME (Minutes)		
• Initial	115	30 Min.
• Final	215	600 Min.
COMPRESSIVE STRENGTH (M Pa)		
• 1 Day	26.9	16 Min.
• 3 Days	38.8	27 Min.

Certified that the cement complies with IS 8041 : 1990

Manager (QUAS)

Vice President(Works)

Works : Anjanipuram, Gudimalkapuram (V), Mellacheruvu (M), Nalgonda (Dist), Telangana State 508 246
Head Office : # 6-3-553, Quena Square, 4th floor, E3 & E4, Erramanzil, Somajiguda, Hyderabad 500 082, Telangana, INDIA.