



An ISO 9001:2015 Company

# Anjani Portland Cement Limited

(A Subsidiary of Chettinad Cement Corporation Pvt. Limited)

## Composite Cement Test Certificate

Ref.: APCL/QUAS/TEST/W.No: 26  
QUAS/F - 26

Date of Despatch: 25.06.2024

Particulars	Test Result	Requirement as per IS 16415 : 2015
<b>CHEMICAL ( As per IS: 4032-1985)</b>		
<ul style="list-style-type: none"><li>• LOI (%)</li><li>• I.R. (%)</li></ul>	<p>3.23 15.91</p>	<p>5.0 Max. Max:<math>X+4(100-X)</math> 100 Min : <math>0.60 \times X</math> (Where X is Declared % of Fly ash)</p>
<ul style="list-style-type: none"><li>• SO<sub>3</sub> (%)</li><li>• MgO (%)</li><li>• Chloride (%)</li><li>• Sulphide Sulphur (%)</li></ul>	<p>2.21 1.26 0.05 0.12</p>	<p>3.5 Max. 8.0 Max. 0.10 Max. 0.75 Max.</p>
<b>PHYSICAL (As per IS: 4031-1988)</b>		
<ul style="list-style-type: none"><li>• Fineness (M<sup>2</sup>/Kg)</li></ul>	356	300 Min.
<b>SOUNDNESS:</b>		
<ul style="list-style-type: none"><li>• Le-Chatlier (mm)</li></ul>	1.0	10 Max.
<ul style="list-style-type: none"><li>• Autoclave (%)</li></ul>	0.022	0.8 Max.
<b>SETTING TIME (Minutes)</b>		
<ul style="list-style-type: none"><li>• Initial</li></ul>	150	30 Min.
<ul style="list-style-type: none"><li>• Final</li></ul>	250	600 Min.
<b>COMPRESSIVE STRENGTH (M Pa)</b>		
<ul style="list-style-type: none"><li>• 3 Days</li><li>• 7 Days</li><li>• 28 Days</li></ul>	<p>26.1 36.3 U.T</p>	<p>23 Min. 33 Min. 43 Min.</p>

Certified that the cement complies  
With IS 16415 : 2015

D.G.M (QUAS & Ope)

Unit Head

Works : Anjanipuram, Gudimalkapuram(Post), Chinthalapalem(V&M), Suryapeta (Dist), Telangana State – 508246  
Head Office : # 6-3-553, Quena Square – 4<sup>th</sup> floor ,E3 & E4 ,Erramanzil , Somajiguda , , Hyderabad -500 082,Telangana,INDIA.