



An ISO 9001:2008 Company

# Anjani Portland Cement Limited

(A Subsidiary of Chettinad Cement Corporation Limited)

## Ordinary Portland Cement 43 Grade Test Certificate

Ref.: APCL/QUAS/TEST/ W.No:04

Date of Despatch: 24.01.17

| Particulars   | Test Result  | Requirement as per IS 8112 : 2013   |
|---|--|---|
| <b>CHEMICAL ( As per IS: 4032-1985)</b>   |  |   |
| <ul style="list-style-type: none"><li>• LOI ( % )</li><li>• I.R. ( % )</li><li>• SO<sub>3</sub> ( % )</li><li>• MgO ( % )</li><li>• Chloride ( % )</li><li>• L.S.F.</li><li>• A/F</li></ul>   | <p>1.72<br/>3.24<br/>2.32<br/>0.85<br/>0.02<br/>0.87<br/>1.18</p>      | <p>5.0 Max.<br/>4.0 Max.<br/>3.5 Max.<br/>6.0 Max.<br/>0.10 Max.<br/>0.66 to 1.02<br/>0.66 Min</p>                  |
| <b>PHYSICAL (As per IS: 4031-1988)</b>  |  |   |
| <ul style="list-style-type: none"><li>• Spec.Surface (M<sup>2</sup>/Kg)</li><li>• SOUNDNESS:<ul style="list-style-type: none"><li>• Le-Chatlier (mm)</li><li>• Autoclave (%)</li></ul></li><li>• SETTING TIME (Minutes)<ul style="list-style-type: none"><li>• Initial</li><li>• Final</li></ul></li><li>• COMPRESSIVE STRENGTH (M Pa)<ul style="list-style-type: none"><li>• 3 Days</li><li>• 7 Days</li><li>• 28 Days</li></ul></li></ul> | <p>271<br/>01<br/>0.048<br/>140<br/>245<br/>33.0<br/>42.8<br/>U.T.</p> | <p>225 Min.<br/>10 Max.<br/>0.8 Max.<br/>30 Min.<br/>600 Min.<br/>23 Min.<br/>33 Min.<br/>43 Min.<br/>58 Max. }</p> |

Certified that the cement complies  
With IS 8112 : 2013

Manager (QUAS )

Vice President (Works)

Works : Anjanipuram, Gudimalkapuram(V), Mellacheruvu(M), Nalgonda (Dist), Telangana State – 508246

Head Office : # 6-3-553, Quena Square – 4<sup>th</sup> floor ,E3 & E4 ,Erramanzil , Somajiguda , , Hyderabad -500 082,Telangana,INDIA.